## **Expert Statement**

No. 555 43422/3e dated 06 May 2010

## Testing according to DIN EN 204 – D3



**Collano Adhesives AG** Client

Eichenstr. 12

6203 Sempach-Station

Switzerland

Order With this expert statement it is confirmed that the results of the testing

> according to DIN EN 204 of an adhesive stated in the test report no. 505 33444/1e are transferrable to the adhesive with the product name "Collano DW 2040" given by the identity statement dated 31.03.2010 and

authority dated 26.03.2010.

**Test results** The evaluations of the partial results of the test report dated 22 May 2007

are presented in the following table.

Load group	Storage sequence	Min. value acc. to EN 204 in N/mm <sup>2</sup>	Mean value of the adhesive strength in N/mm <sup>2</sup>
D3	1	≥ 10	12.1
D3	3	≥ 2	2.8
D3	4	≥ 8	14.1

On the basis of the determined values the adhesive "Collano DW 2040" may be classified in durability class D3 according to DIN EN 204 and thus may be marked

Adhesive DIN EN 204 - D3

ift Rosenheim 06 May 2010

Karin Lieb, Dipl.-Ing. (FH) **Head of Testing Department** ift Centre Glass, Building Materials &

**Building Physics** 

Dr. Odette Moarcas

Test engineer

ift Centre Glass, Building Materials &

**Building Physics**