

Collano BM 833

Universal MS polymer mounting adhesive,
easy to process and high initial tack

Characteristics

Base

Silan-terminated polymer

Colour

White

Density

1.59 g/cm³

Solids content

100%

Fluidity

Non-sag

Form

Liquid

Storage

18 months in unopened original packaging at 15–25 °C

Application area and materials

For large-area applications of lightweight construction, insulation and insulating materials as well as for glass, mirrors, natural stone, metal, lead, aluminium, various plastics and stair mounting. Indoors and protected from direct weathering outdoors. Not suitable for Plexiglas, PP, PE, Teflon.

Performance and material properties

Information derives from tests carried out by Collano. Further information on request.

Tensile strength

1.6 N/mm², DIN 53504

Elongation at break

200%, DIN 53504

Modulus of elasticity

1.5 N/mm², DIN 53504

Hardness

Shore A 57, EN 53505

Temperature resistance

-40 °C to +90 °C

Eco label

EC1^{PLUS}, premium class – very low emission
eco 2, well suited for Minergie-ECO

Packaging

Cartridges 290 ml

Application data

The curing behaviour of MS polymer adhesives depends on the moisture content and temperature of the adherends and the ambient climate. The figures are based on results of tests made under standard conditions (20 °C and 65% relative humidity). Different conditions may lead to deviations from the said specifications.

Application temperature

5–35 °C

Shining time

< 10 minutes

Through-hardening time

1.5–2 mm per 24 hours

Application

Apply triangular beads vertically using cartridge gun and the supplied V-nozzle applicator. Press together up to a joint width of 1–5 mm. Space beads 10–20 cm apart, depending on type and weight of the adherend. For optimum joint quality, it is essential that the surfaces be clean and free of grease.

Additional details

Yield 290 ml cartridge:

V-nozzle applicator Running meters

Triangular beads 6 m

Clean-up

Uncured adhesive can be removed with Collano HP 3000, Collano HP 3100 or ethanol, cured adhesive, remove mechanically. For further information on cleaning, please refer to the flyers on "Pretreatment and Cleaning of PUR Adhesives".

Safety

The wearing of protective gloves and safety goggles is recommended while handling the liquid product. Follow the instructions on the Safety Data Sheet.

The current data sheets are available at:

collano.com/en/downloads

Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our long standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that Collano's technical support service be consulted first. Collano's general sales and delivery terms and conditions shall apply.

Collano AG

6203 Sempach Station · Switzerland · T +41 41 469 92 75
info@collano.com · www.collano.com