

Collano HP 2200

Release Agent for Veneer Adhesives

Characteristics

Base

Oil-wax emulsion

Colour

White

Density

0.95 g/cm³

pH value

7

Form

Liquid

Storage

18 months in the unopened original packaging at 15–25 °C (frost susceptible)

Application area and materials

Prevents adhesives from sticking to veneering presses, press fixtures, compression moulds, press belts, contact rollers and frame presses. Veneered surfaces do not stick to pressing plates. Adhesive residue can be removed easily. No spots remain on veneer surfaces.

Application

Apply an even, thin coat of Collano HP 2200 to the surfaces using a clean cloth or brush, and let it act. The effectiveness (film formation) is good at surface temperatures above 60 °C, and optimal at 90–120 °C.

Clean-up

Remove Collano HP 2200 using soapy water or solvent.

Safety

The wearing of protective gloves and safety goggles is recommended while handling the product. Follow the instructions on the Safety Data Sheet.

Packaging

Plastic pails 5 kg

The current data sheets are available at:

collano.com/en/downloads

Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our long standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that Collano's technical support service be consulted first. Collano's general sales and delivery terms and conditions shall apply.

Collano AG

6203 Sempach Station · Schweiz · T +41 41 469 92 75
info@collano.com · www.collano.com