

Collano HP 7000

Swarf Binder

Characteristics

Base

Nitrocellulose in solvent

Colour

Transparent

Density

0.84 g/cm³

Viscosity (Brookfield)

900 mPa·s

Form

Liquid

Flammability

Inflammable

Storage

24 months in unopened original packaging
at 15–25 °C

Application data

Adhesive application quantity

Approx 1 lt/10 m²

Application temperature

> 12 °C

Application area and materials

For binding swarf to fill and smooth cracks, joints and indentations.

Application

Mix sawdust (made of the same wood, where possible, and free of wax and dirt) with Collano HP 7000 to form a spreadable paste and apply it. Follow by fine-sanding so that the surface of the binder filler is smooth and even.

Safety

Use only in well-ventilated areas. The wearing of protective gloves and safety goggles is recommended while handling the product. Follow the instructions on the Safety Data Sheet.

Packaging

Tin bucket 1 lt

Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our long standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that Collano's technical support service be consulted first. Collano's general sales and delivery terms and conditions shall apply.

Collano AG

CH-6203 Sempach Station · T +41 41 469 92 75
verkauf@collano.com · www.collano.com