

# Semparoc Rapid V

1C PUR adhesive, high water- and heat-resistance

## Characteristics

### Base

Polyurethane

### Colour

Light beige

### Density

1.15 g/cm<sup>3</sup>

### Solids content

100%

### Fluidity

Free flowing

### Viscosity (Brookfield)

10'000–14'000 mPa·s

### Form

Liquid

### Storage

9 months in unopened original packaging at 15–25 °C



## Application area and materials

For common European woods and wood materials, synthetics, stone, ceramics, metals, insulating materials, concrete and non-flammable building boards. For tropical timber and woods with a high content of ingredients, we recommend performing bonding tests. For applications in exposed areas it is essential to seek clarification on the parts' intended use and to perform bonding tests.

## Performance and material properties

Information derives from tests carried out by Collano. Further information on request.

### Bond strength

EN 12765, stress group C4

### Temperature resistance

120 °C at short-term temperature stability

### Fire resistance category

EN 13501, provided the appropriate materials and constructions are used

### Resistance

Resistant against weak caustics, acids and solvents

### Eco label

ecoBasis, does not violate any Minergie-ECO exclusion criteria

## Packaging

Plastic bottles 800 g

Metal drums 250 kg

## Application data

The curing behaviour of 1C PUR adhesives depends on the moisture content and temperature of the adherends and the ambient climate. The figures are based on results of tests on precision bonds (wood moisture content 12%) made under standard conditions (20 °C and 65% relative humidity). Different conditions may lead to deviations from the said specifications.

### Adhesive application quantity

100–300 g/m<sup>2</sup>

### Pressure

0.1–1.0 N/mm<sup>2</sup>

### Material moisture content

6–18%

### Application temperature

10–30 °C

### Maximum open assembly time

< 15 minutes

### Minimum press time

> 45 minutes

### Final strength

7 days

## Application

It is essential that the surfaces are clean and grease-free in order to provide the best adhesion and quality of join. Apply the adhesive directly from the container and spread using the appropriate Collano spatula. The adherends should first be conditioned to match the climatic conditions of the intended application area, before gluing.

## Clean-up

Wipe off any splashes of liquid adhesive using Collano HP 3000, Collano HP 3100 or ethanol. Remove cured adhesive using Collano HP 3000.

### Preventing and blocking adhesion

Collano HP 2000 can prevent adhesion to equipment, tools and machinery. For further information on cleaning and adhesion, please refer to the flyers on "Pretreatment and Cleaning of PUR Adhesives".

## Safety

The wearing of protective gloves and safety goggles is recommended while handling the liquid product. Follow the instructions on the safety data sheet.

**The current data sheets are available at:**

[collano.com/en/downloads](https://collano.com/en/downloads)

### Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our long standing experience with the recommended applications under the specified conditions. Material, processing, and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that Collano's technical support service be consulted first. Collano's general sales and delivery terms and conditions shall apply.